



SHIELDALL 1050

Resistance to Fungus and Mold Growth

ASTM D 5590 Test Results

Note: ASTM D 5590 is a severe test with the test samples placed directly onto a nutritive agar food source, and kept at 28C under 85-90%RH. The total surface of the sample and agar is inoculated with fungi spores of Aspergillus niger, Penicillium funiculosum, and Aureobasidium pullulans. A rating of zero means no growth, 1 means trace growth of up to 10% surface coverage, 2 means light growth of 10-30%, 3 means moderate growth of 30-60%, and a 4 rating means over 60% to heavy growth over the surface.

Coverage Rate	Rating	Zone of Inhibition
TSR #20061130-001		
Applied onto the surface of pine wood		
1. 1000 square feet/gallon	0, 0	8-18
2. Control, untreated pine wood	4, 4	none
Applied onto the surface of gypsum wallboard facing		
1. 1000 square feet/gallon	0, 0	0-8 mm
2. Control, untreated wallboard facing	4.0, 2.5	none

Reported by:
Vern Batdorf
Technical Director
January 08, 2007